

**schedule 5 for Plain-End Pipe**  
**(Data from ASME B36.10 (incorporating ASTM A53 Table 2.2))**

DN	NPS	Outside Diameter		Wall Thickness		Plain End Mass		Identification	Schedule No.
		mm	in	mm	in	kg/m	lb/ft		
15	1/2	21.3	0.840	1.65	0.065	0.80	0.54		5
20	3/4	26.7	1.050	1.65	0.065	1.03	0.69		5
25	1	33.4	1.315	1.65	0.065	1.29	0.87		5
32	1 1/4	42.2	1.660	1.65	0.065	1.65	1.11		5
40	1 1/2	48.3	1.900	1.65	0.065	1.90	1.28		5
50	2	60.3	2.375	1.65	0.065	2.39	1.61		5
65	2 1/2	73.0	2.875	2.11	0.083	3.69	2.48		5
80	3	88.9	3.500	2.11	0.083	4.52	3.03		5
90	3 1/2	101.6	4.000	2.11	0.083	5.18	3.48		5
100	4	114.3	4.500	2.11	0.083	5.84	3.92		5
125	5	141.3	5.563	2.77	0.109	9.46	6.36		5
150	6	168.3	6.625	2.77	0.109	11.31	7.59		5
200	8	219.1	8.625	2.77	0.109	14.78	9.92		5
250	10	273.0	10.750	3.4	0.134	22.61	15.21		5
300	12	323.8	12.750	3.96	0.156	31.24	21.00		5
350	14	355.6	14.000	3.96	0.156	34.34	23.09		5
400	16	406.4	16.000	4.19	0.165	41.56	27.93		5
450	18	457	18.000	4.19	0.165	46.79	31.46		5
500	20	508	20.000	4.78	0.188	59.32	39.82		5
550	22	559	22.000	4.78	0.188	65.33	43.84		5
600	24	610	24.000	5.54	0.218	82.58	55.42		5
750	30	762	30.000	6.35	0.250	118.34	79.51		5